



| PIPE SIZE (N.B) | DN | CODE | C | A | B |
|-----------------|-----|-------------|-----|-----|-------|
| 10 | 250 | GE10.010FF3 | 350 | 395 | 276.5 |
| 12 | 300 | GE12.010FF3 | 400 | 445 | 327.5 |

** DIMENSIONS SUBJECT TO CHANGE - PLEASE CONTACT US IF CRITICAL **

Material Data Sheet

Material Reference

2349

Colour

BLACK

To Specification

COMMERCIAL

| Basic Properties | Value | Test Method | Unit |
|--|------------------|--------------------|---------|
| Base Polymer Type | SBR/EPDM | | |
| Indentation Hardness | 60 Shore A -4 +5 | ASTM D2240 00 | Degrees |
| Specific Gravity | 1.5 +/- 0.05 | ASTM D792 | g/cm3 |
| Tensile Strength - Minimum | 3 | ASTM D412 | Mpa |
| Elongation @ Break - Minimum | 250 | ASTM D412 | % |
| Minimum Continuous Working Temperature | -20 | | °C |
| Maximum Continuous Working Temperature | 70 | | °C |
| Maximum Intermittent Working Temperature | 90 | | °C |
| Compression Set 70 Degrees 22 Hours | 30% Max | ASTM D395 Method B | % |
| Insertion Type | None | | |

Guidelines for Use (It is the Customers responsibility to ensure suitability of Use)

| | |
|--------------------------|-----------------|
| Food Use Suitability | Not Recommended |
| Abrasion Resistance | Moderate |
| Ozone Weather Resistance | Moderate |
| Flame Retardency | Not Recommended |
| Electrical Resistance | Not Recommended |
| General Purpose | Not Recommended |



5 STAR ★★★★★
CUSTOMER SERVICE



SAME DAY DISPATCH -
ORDERS PLACED BEFORE 4:30PM



WEALTH OF
INDUSTRY KNOWLEDGE



ONE OF THE LARGEST
STOCKISTS IN THE UK