



PIPE SIZE (N.B)	DN	CODE	C	A	B
1/2	15	GE0.5EFF3	66.68	95.25	22.35
3/4	20	GE0.75EFF3	73.03	101.6	27.69
1	25	GE1.0EFF3	82.55	114.3	34.54
1.25	32	GE1.25EFF3	87.31	120.65	43.18
1.5	40	GE1.5EFF3	98.43	133.35	49.53
2	50	GE2.0EFF3	114.3	152.4	61.98
2.5	65	GE2.5EFF3	127	165.1	74.68
3	80	GE3.0EFF3	146.05	184.15	90.68
4	100	GE4.0EFF3	177.8	215.9	116.08
5	125	GE5.0EFF3	209.55	254	143.76
6	150	GE6.0EFF3	234.95	279.4	170.69
8	200	GE8.0EFF3	292.1	336.55	221.48
10	250	GE10.0EFF3	355.6	406.4	276
12	300	GE12.0EFF3	406.4	457.2	327

** DIMENSIONS SUBJECT TO CHANGE - PLEASE CONTACT US IF CRITICAL **

Material Data Sheet

Material Reference

2349

Colour

BLACK

To Specification

COMMERCIAL

Basic Properties	Value	Test Method	Unit
Base Polymer Type	SBR/EPDM		
Indentation Hardness	60 Shore A -4 +5	ASTM D2240 00	Degrees
Specific Gravity	1.5 +/- 0.05	ASTM D792	g/cm3
Tensile Strength - Minimum	3	ASTM D412	Mpa
Elongation @ Break - Minimum	250	ASTM D412	%
Minimum Continuous Working Temperature	-20		°C
Maximum Continuous Working Temperature	70		°C
Maximum Intermittent Working Temperature	90		°C
Compression Set 70 Degrees 22 Hours	30% Max	ASTM D395 Method B	%
Insertion Type	None		

Guidelines for Use (It is the Customers responsibility to ensure suitability of Use)

Food Use Suitability	Not Recommended
Abrasion Resistance	Moderate
Ozone Weather Resistance	Moderate
Flame Retardancy	Not Recommended
Electrical Resistance	Not Recommended
General Purpose	Not Recommended



5 STAR ★★★★★
CUSTOMER SERVICE



SAME DAY DISPATCH -
ORDERS PLACED BEFORE 4:30PM



WEALTH OF
INDUSTRY KNOWLEDGE



ONE OF THE LARGEST
STOCKISTS IN THE UK