



PIPE SIZE (N.B)	DN	CODE	C	A	B
10	250	GE10.010FF3	350	395	276.5
12	300	GE12.010FF3	400	445	327.5
14	350	GE14.010FF3	460	505	359.5
16	400	GE16.010FF3	515	565	410.5

**** Dimensions subject to change - Please contact us if critical ****

Material data sheet

Material Reference	2349
Colour	Black
To Specification	Commercial

Basic Properties	Value	Test Method	Unit
Base Polymer Type	SBR/EPDM		
Indentation Hardness	60 Shore A -4 +5	ASTM D2240 00	Degrees
Specific Gravity	1.5 +/- 0.05	ASTM D792	g/cm ³
Tensile Strength - Minimum	3	ASTM D412	Mpa
Elongation @ Break - Minimum	250	ASTM D412	%
Minimum Continuous Working Temperature	-20		°C
Maximum Continuous Working Temperature	70		°C
Maximum Intermittent Working Temperature	90		°C
Compression Set 70 Degrees 22 Hours	30% Max.	ASTM D395 Method B	%
Insertion Type	None		

Guidelines for Use (It is the customers responsibility to ensure suitability of use)	
Food Use Suitability	Not Recommended
Indentation Hardness	Moderate
Ozone Weather Resistance	Moderate
Flame Retardency	Not Recommended
General Purpose	Not Recommended