



PIPE SIZE (N.B)	DN	CODE	C	A	B
FOR 3" AND BELOW USE PN16					
4	100	GE4.040FF3	190	235	116
5	125	GE5.040FF3	220	270	141.5
6	150	GE6.040FF3	250	300	170.5

\*\* DIMENSIONS SUBJECT TO CHANGE - PLEASE CONTACT US IF CRITICAL \*\*

### Material Data Sheet

#### Material Reference

2349

#### Colour

BLACK

#### To Specification

COMMERCIAL

Basic Properties	Value	Test Method	Unit
Base Polymer Type	SBR/EPDM		
Indentation Hardness	60 Shore A -4 +5	ASTM D2240 00	Degrees
Specific Gravity	1.5 +/- 0.05	ASTM D792	g/cm3
Tensile Strength - Minimum	3	ASTM D412	Mpa
Elongation @ Break - Minimum	250	ASTM D412	%
Minimum Continuous Working Temperature	-20		°C
Maximum Continuous Working Temperature	70		°C
Maximum Intermittent Working Temperature	90		°C
Compression Set 70 Degrees 22 Hours	30% Max	ASTM D395 Method B	%
Insertion Type	None		

#### Guidelines for Use (It is the Customers responsibility to ensure suitability of Use)

Food Use Suitability	Not Recommended
Abrasion Resistance	Moderate
Ozone Weather Resistance	Moderate
Flame Retardancy	Not Recommended
Electrical Resistance	Not Recommended
General Purpose	Not Recommended



5 STAR ★★★★★  
CUSTOMER SERVICE



SAME DAY DISPATCH -  
ORDERS PLACED BEFORE 4:30PM



WEALTH OF  
INDUSTRY KNOWLEDGE



ONE OF THE LARGEST  
STOCKISTS IN THE UK